

Goldspar Satin

Varnishes

Quick Drying Satin Yacht Varnish Professional wipe down solvent designed to remove surface



PRODUCT DESCRIPTION

Goldspar Satin is a one-component interior satin varnish that is quick drying which helps to reduce dust pick up. This traditional varnish provides a hard smooth satin finish which is resistant to mild acids & alkalis.

PRODUCT INFORMATION

Colour	YVA251
Finish	Satin
Specific Gravity	0.900
Volume Solids	46%
Typical Shelf Life	2 yrs
VOC (As Supplied)	425 g/lit
Unit Size	375 ml 750 ml 2.5 Lt

DRYING/OVERCOATING INFORMATION

		Drying							
		5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry		5 hrs		3 hrs		1 hrs		30 mins	
Overcoated By		Overcoating Substrate Temperature							
		5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
		Min	Max	Min	Max	Min	Max	Min	Max
Goldspar Satin		24 hrs	4 days	15 hrs	3 days	6 hrs	2 days	3 hrs	1 days

APPLICATION AND USE

Preparation	PREVIOUSLY VARNISHED WOOD In Good Condition Clean with thinners. Sand smooth with 280-320 grade paper. Remove sanding dust with thinners. In Poor Condition Remove all previous coatings. BARE WOOD Ensure that the surface is thoroughly degreased. Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat. Priming bare wood: Thin the first coat by 10-15% with Thinner No.1.
Method	Apply a minimum of 3 unthinned coats, more if using a roller. Avoid using direct from the can. Pour the amount you expect to use in a separate container.
Hints	Mixing Stir well before use. Thinner Thinner No.1, Thinner No.3 Cleaner Thinner No.1 Airless Spray (Professional spray application only) Pressure: 176-210 bar. Tip Size: 1365-1580. Conventional Spray (Professional spray application only) Pressure: 2-3 bar. Tip Size: 1.1-1.4 mm. Thin 25-30% with Thinners No.3 Roller If applying by roller, lay off with a brush or pad otherwise air bubbles may become trapped in the film. Other For Airmix spray application: Pressure: 2 bar. Tip Size: 06-113. For best results sand lightly between coats with 320-400 grade paper. Avoid using direct from the can. Pour the amount you expect to use in a separate container.
Some Important Points	Only use recommended thinners. Use above the waterline only. Avoid painting in direct sunlight. Product temperature should be minimum 15°C and maximum 35°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for use on all types of wood as long as correct surface preparation has been carried out.
Number of Coats	3 minimum
Coverage	(Theoretical) - 11.5 m²/L per coat (Practical) - 10.3 m²/L per coat
Recommended DFT per coat	40 microns dry by brush
Recommended WFT per coat	87 microns wet by brush
Application Methods	Brush, Roller, Airmix, Airless Spray, Conventional Spray (Professional spray application only)

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.

Goldspar Satin

Varnishes

Quick Drying Satin Yacht Varnish Professional wipe down solvent designed to remove surface



TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Goldspar Satin to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Goldspar Satin should be kept in securely closed containers during transport and storage.

Safety

GENERAL:

Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Goldspar Satin cannot be disposed of through the municipal waste route or dumped without permit.

Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.